

## Article

# Biomimetic Catalysts Based on Au@ZnO-Graphene Composites for the Generation of Hydrogen by Water Splitting

Abniel Machín<sup>1\*</sup>, Juan C. Arango<sup>2</sup>, Kenneth Fontánez<sup>2</sup>, María Cotto<sup>2</sup>, José Duconge<sup>2</sup>, Loraine Soto-Vázquez<sup>3</sup>, Edgard Resto<sup>3</sup>, Florian I. Petrescu<sup>4</sup>, Carmen Morant<sup>5</sup>, and Francisco Márquez<sup>2</sup>

<sup>1</sup> Arecibo Observatory, Universidad Ana G. Méndez-Cupey Campus, 00926PR, United States

<sup>2</sup> Nanomaterials Research Group, School of Natural Sciences and Technology, Universidad Ana G. Méndez-Gurabo Campus, 00778PR, United States

<sup>3</sup> Materials Characterization Center Inc., Molecular Sciences Research Center, University of Puerto Rico, 00926PR, United States

<sup>4</sup> IFToMM-ARoTMM, Bucharest Polytechnic University, Bucharest, (CE), Romania

<sup>5</sup> Department of Applied Physics, Autonomous University of Madrid, 28041, Spain

\* Correspondence: [machina1@uagm.edu](mailto:machina1@uagm.edu)

Received: date; Accepted: date; Published: date

**Abstract:** For some decades, the scientific community has been looking for alternatives to the use of fossil fuels that allow the planet's sustainable and environmentally friendly development. To do this, attempts have been made to mimic some processes that occur in nature, among which the photosystem-II stands out, which allows water splitting operating with different steps to generate oxygen and hydrogen. This research presents promising results using synthetic catalysts, which try to simulate some natural processes, and which are based on Au@ZnO-graphene compounds. These catalysts were prepared by incorporating different amounts of gold nanoparticles (1 wt.%, 3 wt.%, 5 wt.%, 10 wt.%) and graphene (1 wt.%) on the surface of synthesized zinc oxide nanowires (ZnO NWs), and zinc oxide nanoparticles (ZnO NPs), along with a commercial form (commercial ZnO) for comparison purposes. The highest amount of hydrogen (1,127  $\mu\text{mol}/\text{hg}$ ) was reported by ZnO NWs with a gold and graphene loadings of 10 wt.% and 1 wt.%, respectively, under irradiation at 400 nm. Quantities of 759  $\mu\text{mol}/\text{hg}$  and 709  $\mu\text{mol}/\text{hg}$  were obtained with catalysts based on ZnO NPs and commercial ZnO, respectively. The photocatalytic activity of all composites increased with respect to the bare semiconductors, being 2.5 times higher in ZnO NWs, 8.8 times for ZnO NPs and 7.5 times for commercial ZnO. The high photocatalytic activity of the catalysts is attributed, mainly, to the synergism between the different amount of gold and graphene incorporated, and the surface area of the composites.

**Keywords:** Hydrogen production; ZnO; gold nanoparticles; graphene; water splitting

## 1. Introduction

If you were asking to identify one of the many challenges that our world is facing right now, you would probably say climate change, energy production or sustainability. Most of these problems are directly related to the continuous growth of world population and the use of fossil fuels as our primary energy source [1].

In the case of finding a clean and renewable energy source, multiple candidates have been proposed over the years. One of them is hydrogen. Some of the properties that make hydrogen a good candidate to replace fossil fuels are its abundance, high energy yield, storage capability, and environmental compatibility [2]. Hydrogen is the most abundant element in the universe and can be found in water and biomass. If compared to hydrocarbons, hydrogen could produce 2.75 times more

energy, could be stored as solid, liquid or gas, and if it is combined with oxygen, no harmful and toxic gases such as nitrogen oxides ( $\text{NO}_x$ ) or sulfur oxides ( $\text{SO}_x$ ) are released to the atmosphere [2].

Unfortunately, the vast majority of hydrogen that is produced in the world, comes from a process known as natural gas reforming [3]. As the name says, this process uses natural gas, methane ( $\text{CH}_4$ ), as the source to obtain hydrogen. This process releases carbon dioxide ( $\text{CO}_2$ ) to atmosphere, increasing the amount of this greenhouse gas and exacerbating global warming [3].

Photosynthesis offers an excellent model for designing an artificial solar energy conversion system for clean fuel generation. In nature, electrons are provided to the reaction center of the photosystem-II in four consecutive proton coupled electron transfer steps, and ultimately appear as reduced carbon derived products that form the basis of biological activity. Inspired by natural principles, for decades there has been a continuous effort to design artificial photosynthetic assemblies based on the use of solar energy to generate oxygen and hydrogen by water splitting [4-6]. Over the years, multiple candidates such as titanium dioxide ( $\text{TiO}_2$ ), zinc oxide ( $\text{ZnO}$ ), tungsten trioxide ( $\text{WO}_3$ ), cadmium sulfide ( $\text{CdS}$ ), among others, have been used to produce hydrogen via water splitting [7,8]. From all these photocatalysts,  $\text{TiO}_2$  has been extensively studied over the years mainly due to its chemical stability, abundance, non-toxicity and high hydrogen yield [7].

As titanium oxide,  $\text{ZnO}$  has also demonstrated to be chemically stable, easy to produce, non-toxic, abundant and environmentally friendly [9,10] although, unlike titanium dioxide,  $\text{ZnO}$  has been widely used for the degradation of organic pollutants and energy storage [9,11,12]. Some authors [13,14] consider that  $\text{ZnO}$  shows some disadvantages for the production of hydrogen by water splitting, especially the recombination of photogenerated electron-hole pairs, fast backward reaction, and the inability to use visible light. To try to solve these limitations different approaches have been implemented over the years. One of them has been the incorporation of noble metal to the surface of the catalysts [13,14]. Among noble metals, gold has gained much attention since the 80's because of its wide range of applications, including electronics, photodynamic therapy, delivery of therapeutic agents, sensors, probes, diagnostics and catalysis [15,16]. Multiples pathways to incorporate gold nanoparticles (Au NPs) can be found in the literature. Methods such as coprecipitation [17], chemical reduction [18], photoreduction [19], and hydrothermal approach [20] have been successfully implemented over the years. All these synthesis procedures take into account parameters such as the preparation procedure, gold loading (percentage of gold weight on the material), particle size, dispersion (percentage of support surface covered by gold), and shape of the particles.

Recently, another approach that has drawn a lot of attention is the use of graphene as a cocatalyst for the production of hydrogen via water splitting. Graphene has unique properties such as high thermal conductivity, excellent mobility of charge carriers, large surface area, and good mechanical stability [21]. As a cocatalyst, graphene has significant advantages, including: i) provides a support for anchoring well-dispersed metallic or oxide nanoparticles; ii) works as a highly conductive matrix for enabling good contact throughout the matrix; iii) induces an easy electron transfer from the conduction band of the semiconductor to graphene because of the large energy level offset formed at the interface, leading to an efficient charge separation; iv) acts as an efficient cocatalyst for  $\text{H}_2$  evolution because of its large specific surface area and superior electron mobility [22].

There are several approaches reported on the literature to prepare graphene- $\text{ZnO}$  composites. For example, Tien and group [23] used a microwave-assisted solvothermal process, whereas Ong and group [24] reported the preparation of the composites using a chemical deposition-calcination approach.

There is very limited information in the literature on the production of hydrogen via water splitting by combining graphene and  $\text{ZnO}$ . Haldorai and Shim [25] reported the production of hydrogen via water splitting by employing a supercritical fluid mediated synthesis. They reported that the composites exhibited enhanced photocatalytic activity because the  $\text{ZnO}$  particles on the graphene sheets captured light energy and acted as electron mediators.

To our knowledge, no results have been reported on the incorporation of graphene and gold nanoparticles on the surface of  $\text{ZnO}$  for the production of hydrogen by water splitting. The information found in the literature is very limited and focuses on the degradation of dyes and

nitrobenzene under visible and UV light. For example, Zeng et al. [26] and Wang et al. [27] reported high photocatalytic activity for the degradation of Rhodamine B and Methylene Blue, respectively. They found that the combination of gold and graphene on the surface of ZnO allows the system to use visible and UV light, and more importantly, greatly improves the degradation percentage compared to pure ZnO and Au-ZnO. On the other hand, Roy et al. [28] reported on the efficient reduction of nitrobenzene under UV and visible light, in which the catalyst reduced 97.8% of the original compound.

Due to the lack of information on the production of hydrogen by water splitting using Au@ZnO-Graphene composites, the objectives of this research focused mainly on: i) synthesizing ZnO with different morphologies (nanoparticles and nanowires); ii) incorporate different amounts of gold nanoparticles (1 wt.%, 3 wt.%, 5 wt.% and 10 wt.%) and graphene (1 wt.%) to the surface of the as-synthesized catalysts and to its commercial form; and iii) characterize the photocatalytic activity of the compounds by studying the production of hydrogen by water splitting under UV-vis radiation. Au@ZnO-Graphene based catalysts were characterized by using HR-TEM, UV-vis spectroscopy, BET surface area, XRD, XPS, Raman spectroscopy, and GC-TCD.

## 2. Materials and Methods

### 2.1. Reagents

All reagents were used as received and all the solutions were prepared using deionized water (Milli-Q water, 18.2 MΩcm<sup>-1</sup> at 25 °C). Zn(CH<sub>3</sub>COO)<sub>2</sub> • 2H<sub>2</sub>O (98+%, ACS Reagent), HAuCl<sub>4</sub>•3H<sub>2</sub>O (ACS Reagent, 49.0+% Au basis), Ethanol (95%) and NaBH<sub>4</sub> (+99.9%) were provided by Sigma Aldrich. NaOH (98+%) and ZnO (99.99%) were acquired from Alfa Aesar. Graphene (99%) was provided by Cheap-Tubes. For photocatalytic experiments, Na<sub>2</sub>S (99.9+%) and Na<sub>2</sub>SO<sub>3</sub> (98+%) were obtained from Sigma Aldrich, and used as sacrificial reagents.

### 2.2. Synthesis of Nanomaterials

ZnO nanowires (ZnO NWs) were obtained according the method described elsewhere [29]. Zinc oxide nanoparticles (ZnO NPs) were synthesized following the method used by Nejati et al. [30]. The deposition of Au NPs and graphene on the surface of ZnO NWs, ZnO NPs and the commercial ZnO (commercial ZnO) is based on the method described by Naldoni et al. [31], later modified by Wang et al. [11]. In a typical synthesis, 200 mg of the product (ZnO NWs, ZnO NPs and commercial ZnO) containing the gold nanoparticles was dispersed in a solution containing 10 mL of ethanol and 40 mL of deionized water, and the mixture was vigorously stirred for 30 minutes. Subsequently, 2 mg of graphene was added, and the suspension was kept under stirring for 1 hour. After that, the product was collected and centrifuged 3 times with deionized water and dried overnight to 60 °C. Finally, the product was collected, sealed and stored at room temperature. The different Au@ZnO-graphene composites were identified as x%Au@ZnO-graphene. The numbers (x%) correspond to the weight percentage of Au NPs in the sample. In all cases, the amount of graphene was 1 wt.%.

### 2.3. Characterization of the Catalysts

The catalysts were characterized by High Resolution Transmission Electron Microscopy (HRTEM), using a JEOL 3000F. XPS measurements were performed on an ESCALAB 220i-XL spectrometer, using the non-monochromated Mg K $\alpha$  (1253.6 eV) radiation of a twin-anode, operating at 20 mA and 12 kV in the constant analyzer energy mode, with a PE of 40 eV. Brunauer Emmett Teller (BET) specific areas were measured using a Micromeritics ASAP 2020, according to N<sub>2</sub> adsorption isotherms at 77 K. Raman (DXR Thermo Raman Microscope, employing a 532 nm laser source at 5 mW power and a nominal resolution of 5 cm<sup>-1</sup>, and X-ray diffraction (Bruker D8 Discover X-ray Diffractometer, operating at 40 kV and 40 mA in the range of 30-75° at 1° min<sup>-1</sup> were also used. UV-vis spectroscopy (Shimadzu UV-2401PC) was used as a complementary technique to determine the absorption edge of the catalysts.


#### 2.4. Photocatalytic experiments

The production of hydrogen via water splitting was measured by adding 50 mg of the x%Au@ZnO-graphene catalyst into 100 mL of deionized water and transferring this suspension to a 250 mL quartz reactor. Then, solutions of 0.02 M Na<sub>2</sub>SO<sub>3</sub> and 0.4 M Na<sub>2</sub>S were added as sacrificial reagents. After that, the solution was thermostatized at 20°C and purged for 30 minutes with nitrogen (N<sub>2</sub>). Finally, the reaction mixture was irradiated with UV-vis light for 2 hours using different filters to select the appropriate wavelength (280 nm, 320 nm, 400 nm, and 500 nm). The produced hydrogen was quantified by gas chromatography (GC), using a thermal conductivity detector (GC-TCD, Perkin-Elmer Clarus 600) [32].

### 3. Results and Discussion

#### 3.1. Characterization of catalysts

The characterization of the different ZnO supports and Au@ZnO based catalysts is shown in our previous research [32]. On these catalysts, 1 wt.% graphene was incorporated. Figure 1 shows the HRTEM images and the Selected Area Electron Diffraction (SAED) patterns of the 10%Au@commercial ZnO-graphene (Figure 1A), 10%Au@ZnO NPs-graphene (Figure 1B), and 10%Au@ZnO NWs-graphene (Figure 1C) composites. The 10%Au@commercial ZnO-graphene composite consists of non-homogenous particles with different sizes (lengths and diameters greater than 50 nm) and shapes. Homogeneous spherical gold nanoparticles, with diameters of less than ca. 10 nm, are distributed on the surface of the catalyst. Graphene sheets of different sizes are also distributed unevenly through the sample. According to Wang et al. [11], it is believed that close and homogeneous contact between Au, support and graphene favors the transfer of photogenerated electrons between them, thus improving charge separation and photocatalytic efficiency. As in the case of the commercial catalyst, the 10%ZnO NPs-graphene catalyst showed non-homogeneous particles of different sizes and shapes, with lengths and diameters greater than 50 nm. The non-homogeneous gold nanoparticles are unevenly distributed throughout the sample, presenting a spherical morphology with diameters of less than 10 nm. Graphene is also unevenly distributed throughout the sample and serves as a support for ZnO particles and gold nanoparticles. In the case of the 10%Au@ZnO NWs-graphene catalyst, the incorporation of graphene and gold considerably modified the pristine material. The catalyst consists of non-homogeneous wires, with an estimated length greater than 300 nm, and diameters above 50 nm. Gold nanoparticles, with spherical morphology and diameters of less than 10 nm, are distributed throughout the sample. Graphene also appears to be unevenly distributed in the sample, but has intimate contact with the gold nanoparticles and the support. SAED patterns of synthesized gold-graphene-based composites are characteristic of monocrystalline materials.



**Figure 1.** HRTEM images of 10%Au@commercial ZnO-graphene (A), 10%Au@ZnO NPs-graphene (B), and 10%Au@ZnO NWs-graphene (C). The red and yellow arrows indicate the presence of graphene and gold, respectively, and the insets correspond to the SAED patterns.

Table 1 shows the BET surface area results of the different Au@ZnO-graphene composites. The incorporation of the different amounts of Au NPs (1 wt.%, 3 wt.%, 5 wt.%, and 10 wt.%), along with graphene (1 wt.%), increased the surface area of all the catalysts when compared to the unmodified supports [32]. This enhancement suggests an intimate contact between the incorporated materials and the support [31]. Graphene, as explained above, has a very high surface area ( $\sim 2,000 \text{ m}^2 \text{ g}^{-1}$ ), which can contribute to increasing the surface area of composites. However, since the amount of graphene, when compared to gold was minimum, the enhancement of the surface areas of the catalysts should be primarily attributed to the Au NPs. The highest surface area of the commercial support was measured to be  $65 \text{ m}^2 \text{ g}^{-1}$ , and was obtained with the 10%Au@ commercial ZnO-graphene. This represents an increase of  $47 \text{ m}^2 \text{ g}^{-1}$  if compared to the unmodified commercial ZnO support. The highest surface area of the Au@ZnO NPs-graphene composites was  $117 \text{ m}^2 \text{ g}^{-1}$ , and was measured in the 10%Au@ZnO NPs-graphene catalyst, showing a difference of  $50 \text{ m}^2 \text{ g}^{-1}$  if compared to the result obtained with the unmodified ZnO NPs. For the Au@ZnO NWs-graphene composites, the highest surface area was  $247 \text{ m}^2 \text{ g}^{-1}$ , obtained by the 10% Au@ZnO NWs-graphene catalyst. This represents a difference of  $80 \text{ m}^2 \text{ g}^{-1}$  if compared to the surface area of the unmodified ZnO NWs ( $167 \text{ m}^2 \text{ g}^{-1}$ ).

The XRD patterns of the different composites with a gold loading of 10 wt.% are shown in Figure 2. The characteristic peaks of wurtzite crystalline phase (ca.  $32^\circ$ (100),  $34.8^\circ$ (002),  $36^\circ$ (101),  $47.5^\circ$ (102),  $56.2^\circ$ (110),  $62.8^\circ$ (103),  $66^\circ$ (200),  $67.5^\circ$ (112),  $68.8^\circ$ (201)) were observed in all the catalysts [12]. In all cases, reflections at  $38.2^\circ$  and  $44.4^\circ$  were observed, which have been associated with Au (111) and (200), respectively [16], indicating that  $\text{Au}^{3+}$  has been reduced to  $\text{Au}^0$ , with the usual fcc structure. Au NPs show other characteristic peaks of lower intensity at  $64.7^\circ$ (220) and  $77.8^\circ$ (311), which could not be identified in the catalysts. Applying the Scherrer formula [33], an estimate of the mean size of the gold nanoparticles could be made, providing a value of ca. 15 nm in all cases. This value is very close

to that determined by HR-TEM (<20 nm). Graphene, on the other hand, has characteristic peaks at ca. 24.5° and 44.2° [20]. These peaks were not identified in any of the composites. The amount of graphene incorporated to the Au@ZnO-Graphene composites was very low when compared to the amount of the support and gold loading, and it is possible that the signal emitted by graphene was very weak and not able to be detected by the instrument.


**Table 1.** BET surface area of the Au@ZnO-graphene composites.

	Commercial ZnO ( $\text{m}^2\text{g}^{-1}$ )	ZnO NPs ( $\text{m}^2\text{g}^{-1}$ )	ZnO NWs ( $\text{m}^2\text{g}^{-1}$ )
<b>Unmodified</b>	18	67	167
<b>1%Au-Graphene*</b>	48	96	201
<b>3%Au-Graphene*</b>	51	103	212
<b>5%Au-Graphene*</b>	56	109	223
<b>10%Au-Graphene*</b>	65	117	247


\* The amount of graphene in all the catalysts was 1 wt.%

The Au@ZnO-graphene composites containing gold loadings of 5 wt.% and 10 wt.% were characterized by Raman spectroscopy (see Figure 3). Graphene has two characteristics peaks at ca. 1350  $\text{cm}^{-1}$  and 1595  $\text{cm}^{-1}$ , known as D and G bands, respectively [10]. The D-band (1350  $\text{cm}^{-1}$ ) has been related to the defects and structural disorder in graphene sheets, whereas the G-band (1595  $\text{cm}^{-1}$ ) has been ascribed to the stretching of the  $\text{sp}^2$  hybridized carbon-carbon bonds [10]. These two bands were observed in all the gold-graphene composites, including those with gold loadings of 1 wt.% and 3 wt.%. The ratio of the intensity between the D and G band is a measure of the degree of disorder in graphene [34]. The narrow strong band at ca. 437  $\text{cm}^{-1}$  ( $E_2$  modes) is present in all the composites and it has been ascribed to motion of Zn in the wurtzite phase [12]. No gold bands were found for any of the composites.


Au@ZnO-graphene composites, with gold loadings of 5 wt.% and 10 wt.%, were also characterized by UV-vis spectroscopy (Figure 4). All the catalysts presented a similar absorption range between 325 nm and 400 nm, showing a maximum at ca. 370 nm. Interestingly, despite the introduction of graphene and gold, all the composites have almost the same absorption edge as the unmodified catalysts, indicating that there is a consistent band gap of nanocrystalline ZnO within the Au@ZnO-graphene composites. This suggests that no carbon species was incorporated into the lattice of ZnO because impurity level would shift the absorption edge to higher wavelength [35]. No gold peaks (~520 – 580 nm) were detected for any of the gold loadings incorporated. This might be attributed to the high dispersity of the Au NPs through the samples.



**Figure 2.** XRD diffraction patterns for 10% Au@commercial ZnO-graphene (a); 10%Au@ZnO NPs-graphene (b); and 10%Au@ZnO NWs-graphene (c).



**Figure 3.** Raman spectra of 5%Au@commercial ZnO-graphene (a); 10%Au@commercial ZnO-graphene (b); 5%Au@ZnO NPs-graphene (c); 10%Au@ZnO NPs-graphene (d); 5%Au@ZnO NWs-graphene (e); and 10%Au@ZnO NWs-graphene (f).




**Figure 4.** UV-vis spectra of different composites: 5%Au@commercial ZnO-graphene (a); 10%Au@commercial ZnO-graphene (b); 5%Au@ZnO NPs-graphene (c); 10%Au@ZnO NPs-graphene (d); 5%Au@ZnO NWs-graphene (e); and 10%Au@ZnO NWs-graphene (f).

The catalysts were also characterized by XPS. Figure 5 shows the most relevant spectra of 10%Au@ZnO NWs-graphene and 10%Au@ZnO NPs-graphene. In both systems (Figures 5a and 5e), the O1s shows a main peak at ca. 530.2 eV, which has been assigned to  $O^{2-}$  ions in the Zn–O bonds, and a shoulder around 531.5 eV, assigned to  $O^{2-}$  ions in the oxygen deficient regions, respectively [32]. As observed, the contribution of this secondary peak is clearly greater in ZnO NWs than in ZnO NPs. As it will be shown later, the highest reactivity is observed in catalysts based on ZnO NWs, so this behavior could be justified thanks to the existence of crystalline defects, as already described in previous works [32]. In fact, surface defects in crystalline ZnO affect its electrical properties, increasing electrical conductivity, which undoubtedly could have positive effects on photocatalysis with these materials. In both catalysts, the Zn2p<sub>3/2</sub> spectra show a single component that has been unambiguously assigned to Zn<sup>2+</sup> in ZnO (see Figures 5b and 5f). The presence of metallic gold (Au<sup>0</sup>) was evidenced by the presence of a doublet in the emission peak at ca. 84 eV (4f<sub>7/2</sub>) and 87.7 eV (4f<sub>5/2</sub>) (Figures 5c and 5g) [36]. No components were observed that could show the presence of Au<sup>3+</sup>, coming from the precursor (HAuCl<sub>4</sub> • 3H<sub>2</sub>O), which evidenced the complete reduction of gold. Figures 5d and 5h show the transition corresponding to C1s. The main peak observed at ca. 284.6 eV is assigned to the carbon backbone of aliphatic/aromatic (sp<sup>3</sup>/sp<sup>2</sup>) carbons, while the component indicated by an arrow, around 286 eV can be attributed to carbon in C–O and C–O–C groups [37,38], and to contamination by adsorption of oxidized species (CO, CO<sub>2</sub>).

### 3.3. Photocatalytic hydrogen production via water splitting

Figure 6 shows the photocatalytic hydrogen production via water splitting of the different catalysts under irradiation at 280 nm (Figure 6a), 320 nm (Figure 6b), 400 nm (Figure 6c), and 500 nm (Figure 6d). The maximum hydrogen production of the unmodified ZnO catalysts was 442  $\mu$ mol/hg and was obtained with ZnO NWs by irradiation at 280 nm. This high hydrogen production from ZnO NWs was not expected, especially when compared to the maximum hydrogen production of ZnO NPs (86  $\mu$ mol/hg) and the commercial ZnO (94  $\mu$ mol/hg). According to a study by Zhang et al. [12], one-dimensional nanostructures, such as nanowires, can enhance the photocatalytic activity due to their large surface-to-volume ratio as compared to other morphologies. Furthermore, ZnO is

considered a promising material for solar cells due to the fast electron transport, with reduced recombination loss, and its ease of crystallization [12].



**Figure 5.** XPS spectra of Zn 2p<sub>3/2</sub>, O 1s, Au 4f and C1s taken from as-grown Au@ZnO NWs-graphene (a - d), and Au@ZnO NPs-graphene (e - h).

Under irradiation at 320 nm, the hydrogen production of ZnO NWs (365  $\mu\text{mol}/\text{hg}$ ) decreased when compared to that obtained at 280 nm, but then increased again (427  $\mu\text{mol}/\text{hg}$ ) at 400 nm. This was not expected either since the wide band gap energy of ZnO (3.37 eV for wurtzite) does not favor the production of hydrogen under visible light. Different studies [39,40,12] have found that surface defects and oxygen vacancies in photocatalysts can play a significant role in their photocatalytic activity. Crystalline defects in ZnO nanowires exist primordially due to oxygen vacancies. Even more, these studies have found that nanoparticles with crystalline defects can exhibit visible light activity even without doping them with transition metals.

Both ZnO NPs and the commercial ZnO obtained similar results in all the wavelengths that were evaluated. At 500 nm, the hydrogen production of the unmodified catalysts was almost zero, with exception of ZnO NWs that obtained a high value of 350  $\mu\text{mol}/\text{hg}$ , showing high catalytic activity. Incorporation of gold and graphene greatly increased hydrogen production in both the UV and visible regions of all the composites. The presence of cocatalysts such as Au and graphene improves the charge separation and suppresses the recombination of excited photogenerated carriers, resulting in a better evolution of H<sub>2</sub> [22]. Different studies [41-43] have demonstrated that when semiconductors, such as ZnO, are doped with noble metal or metal ions, they exhibit a negative shift in the Fermi level that implies a greater degree of electron accumulation in Au-loaded. Thus, such a shift in the Fermi level improves the composite system and enhances the efficiency of the interfacial charge-transfer process. These improvements are in turn associated with a considerable enhancement of the electric near-field [41]. This activity relates strongly to the size and shape-dependent surface charge oscillation known as Surface Plasmon Resonance (SPR) in the presence of light irradiation [22]. Furthermore, the incorporation of graphene on semiconductors creates the p-n junction, which also improves the separation of photogenerated charges [22,44]. The photogenerated holes that were created are then scavenged by the sacrificial agent (S<sup>2-</sup>/SO<sub>3</sub><sup>2-</sup>), and the electrons are excited to the conduction band. Electrons transferred from the conduction band of the semiconductor are injected into the graphene because graphene has a slightly lower redox potential than the semiconductor conduction band [22,44]. Graphene has a high charge carrier transfer and mobility as a result of its  $\pi$ -conjugated structure, and hence Au nanoparticles dispersed on the graphene can also accept electrons and act as active sites to react with adsorbed H<sup>+</sup> ions for H<sub>2</sub> evolution [22,44].

According to other authors [10,45], some conduction electrons can be transferred directly to the Au NPs deposited on the surface of the semiconductor by ohmic interconnection or to carbon atoms on the graphene, and the electrons then react with the adsorbed H<sup>+</sup> ions to form H<sub>2</sub>. Thus, the synergistic effect between both cocatalysts, plasmonic Au nanoparticles and graphene, can effectively

suppress photogenerated charge recombination, enlarge the active adsorption sites and reaction space, and consequently enhance the photocatalytic activity for H<sub>2</sub> evolution [10,45]. In this regard, Wang et al. [45] reported that Au@TiO<sub>2</sub>-graphene composites had significantly increased the visible light absorption and enhanced the photocatalytic H<sub>2</sub> production activity compared to the Au@TiO<sub>2</sub>. Luo et al. [10] found that by combining graphene and gold nanoparticles on TiO<sub>2</sub>-P25, the hydrogen production via water splitting increased nine times more than bare TiO<sub>2</sub>-P25.

In this research, the highest hydrogen production of the Au@commercial ZnO-graphene catalysts was 709 μmol/hg and was obtained by 10%Au@ZnO commercial-Graphene under irradiation at 400 nm. This enhancement represents a difference of 615 μmol/hg when compared to the highest amount obtained by the unmodified commercial ZnO catalyst (94 μmol/hg), and the fact that the maximum production of the commercial catalyst was obtained at 400 nm (visible light) is an indication that the Au NPs are allowing the use of visible light [14,26,10]. On the other hand, appropriate visible light irradiation can induce the SPR effect on the gold nanoparticles and greatly enhance the electron capture capacity [10]. Both reasons affect the generation and separation of charges in photocatalysis, which results in the improvement of photocatalytic properties. The highest amount of hydrogen obtained with 1%Au@commercial ZnO-graphene, 3%Au@commercial ZnO-graphene and 5%Au@commercial ZnO-graphene catalysts was 405 μmol/hg, 529 μmol/hg and 589 μmol/hg respectively, under irradiation at 400 nm.

In the case of Au@ZnO NPs-graphene catalysts, the highest hydrogen production measured was 759 μmol/hg, representing a difference of 673 μmol/hg when compared to the maximum hydrogen production of the unmodified ZnO NPs catalyst (86 μmol/hg), and was obtained with the 10%Au@ZnO NPs-graphene catalyst at 400 nm. The highest hydrogen production for 1%Au@ZnO NPs-graphene, 3%Au@ZnO NPs-graphene and 5%Au@ZnO NPs-graphene catalysts was 537 μmol/hg, 622 μmol/hg and 728 μmol/hg, respectively. These results confirm once again that the presence of Au NPs allows the use of visible light to produce hydrogen.


Au@ZnO NWs-graphene catalysts showed the highest hydrogen production (1,127 μmol/hg) with a gold loading of 10 wt.% at 400 nm, representing a difference of 685 μmol/hg when compared to the unmodified ZnO NWs catalyst (442 μmol/hg). The highest amount of hydrogen produced at 400 nm with the 1%Au@ZnO NWs-graphene, 3%Au@ZnO NWs-graphene and 5%Au@ZnO NWs-graphene catalysts was 701 μmol/hg, 828 μmol/hg and 944 μmol/hg, respectively.

Under irradiation at 500 nm (Figure 6d), the maximum hydrogen production of the Au@commercial ZnO-graphene, Au@ZnO NPs-Graphene and Au@ZnO NWs-Graphene catalysts was 628 μmol/hg, 735 μmol/hg and 1,079 μmol/hg, respectively, with a gold loading of 10 wt.%. These high hydrogen productions under low energy irradiation is an indication of the high photocatalytic activity of the composites, especially considering the high band-gap energy (3.37 eV) of ZnO. At wavelengths above 400 nm, the water splitting depends mainly on the Au NPs, due to lack of energy to promote electrons from the valence band to the conduction band of ZnO.

In all cases, the highest amounts of hydrogen reported in this investigation were obtained with the catalysts with the highest surface area (65 m<sup>2</sup>g<sup>-1</sup> for 10%Au@ commercial ZnO-graphene; 117 m<sup>2</sup>g<sup>-1</sup> for 10%Au@ZnO NPs-graphene; 247 m<sup>2</sup>g<sup>-1</sup> for 10%Au@ZnO NWs-graphene). Materials with high surface areas can be attained either by fabricating small particles or clusters where the surface-to-volume ratio of each particle is high, or by creating materials where the void surface area (pores) is high compared to the amount of bulk support material [46]. Multiple studies have demonstrated that the synthesis of high surface area catalysts lead to an increment in the hydrogen production due to the availability of more sites for the interaction of the water molecule with the catalyst [45]. In our research, this increase in surface area is primarily achieved by incorporating Au NPs and graphene on the surface of semiconductors.

In the case of Au/graphene-TiO<sub>2</sub>, over the years different possible mechanisms have been proposed for the production of hydrogen by water splitting. One of the most widely accepted is that when compounds are irradiated with UV light, a direct photoexcitation of TiO<sub>2</sub> with photons with energy larger than the bandgap ( $\lambda < 380$  nm) leads to the generation of electrons in the conduction band, and electron holes in the valence band of the semiconductor [47]. The electron in the conduction

band will move to the Au NPs, acting as electron buffers and catalytic sites for hydrogen generation [48]. When irradiate with visible light ( $\lambda > 500$  nm) photoexcitation of Au NPs occurs and electrons from the Au NPs are injected into the  $\text{TiO}_2$  conduction band leading to the generation of holes in the Au NPs and electrons in the  $\text{TiO}_2$  conduction band [47,48]. Then, the water molecule gains the electrons in the conduction band and hydrogen is produced. Evidence of the proposed mechanism is the fact that the photocatalytic response for hydrogen generation is consistent with the absorption of the Au surface plasmon band. The incorporation of graphene creates a p-n junction, which improves the separation of photogenerated charges, and the electrons are excited to the conduction band [22]. The electrons transferred from the conduction band of  $\text{TiO}_2$  are injected into the reduced graphene in a graphene/ $\text{TiO}_2$  system because the graphene/graphene redox potential is slightly lower than the CB of  $\text{TiO}_2$  [22]. In addition, some conduction electrons of  $\text{TiO}_2$  likely transfer directly to the Au NPs deposited on the surface of the semiconductor by ohmic interconnection or to carbon atoms on the graphene sheets, and the electrons then react with the adsorbed  $\text{H}^+$  ions to form  $\text{H}_2$  [22, 21]. This creates a synergistic effect between both cocatalysts, and they can effectively suppress photogenerated charge recombination, enlarge the active adsorption sites, and consequently enhance the photocatalytic activity [22, 21,11].



**Figure 6.** Photocatalytic hydrogen production of the different  $\text{Au@ZnO}$ -graphene catalysts under irradiation at 280 nm (a), 320 nm (b), 400 nm (c) and 500 nm (d).

Table 2 shows the highest amounts of hydrogen obtained with  $\text{Au@ZnO}$ -graphene catalysts under the evaluated parameters. As already mentioned, and to the best of our knowledge, no results have been reported so far on hydrogen production by water splitting using  $\text{Au@ZnO}$ -graphene

catalysts. Therefore, the results of this research, are the first reported on the production of H<sub>2</sub> using catalysts based on ZnO and graphene-gold. The materials studied in this research will have to be contrasted by other researchers to establish a much deeper knowledge that allows us to know the complex mechanism of hydrogen production with ternary compounds based on ZnO.

**Table 2.** Highest amounts of hydrogen production via water splitting obtained with Au@ZnO-Graphene catalysts under UV-vis light.

Author	H <sub>2</sub> production (μmol)	Source (nm)	Irradiation time (h)	ZnO Crystal structure *	Reaction Mixture	Au (wt.%)	Graphene (wt.%)
This work ZnO commercial	709	200>1>400	2	W	Water: 0.5M Na <sub>2</sub> S, 0.03M Na <sub>2</sub> SO <sub>3</sub>	10	1
This work ZnO NPs	759	200>1>400	2	W	Water: 0.5M Na <sub>2</sub> S, 0.03M Na <sub>2</sub> SO <sub>3</sub>	10	1
This work ZnO NWs	1127	200>1>700	2	W	Water: 0.5M Na <sub>2</sub> S, 0.03M Na <sub>2</sub> SO <sub>3</sub>	10	1

\*W = Wurtzite

#### 4. Conclusions

Graphene and different amounts of gold nanoparticles were incorporated on the surface of synthesized ZnO supports (ZnO NWs, ZnO NPs catalysts), and on the commercial form (commercial ZnO). These catalysts were fully characterized by different techniques, and their photocatalytic activity was determined by measuring the hydrogen produced by water splitting under UV-vis irradiation.

The highest amount of the unmodified ZnO support was 442 μmol/hg and was obtained by the ZnO NWs catalyst under irradiation at 280 nm. This unexpectedly high hydrogen production may be attributed to the morphology (nanowires) and possible defects in the crystalline structure. The maximum hydrogen production for the ZnO NPs and commercial ZnO catalysts was 94 μmol/hg and 86 μmol/hg, respectively, at 280 nm.

The maximum hydrogen production obtained with the commercial ZnO composites containing gold and graphene was 709 μmol/hg at 400 nm, and was obtained with a gold loading of 10 wt%. The enhancement in the hydrogen production was 7.5 times higher than that reported by the commercial ZnO.

The higher hydrogen production for the Au@ZnO NPs-graphene catalysts was 759 μmol/hg at 400 nm, and was obtained with 10%Au@ZnO NPs-graphene. The enhancement in the hydrogen production was 8.8 times higher than that reported by the ZnO NPs catalyst.

In the case of the Au@ZnO NWs-graphene composites, the higher hydrogen production (1,127 μmol/hg) was obtained with the 10%Au@ZnO NWs-graphene under irradiation at 400 nm.

The catalysts did not show a reduction in the surface area nor in the hydrogen production with the increment in gold loadings and incorporation of graphene. These results suggest that the best graphene and gold loading for the Au@ZnO-graphene catalysts could be higher than 1 and 10 wt.%, respectively.

**Author Contributions:** Conceptualization, A.M., F.M.; methodology, A.M., F.M.; formal analysis, A.M., F.M.; investigation, A.M., J.A.; K.F. L.S.; E.R., C.M.; resources, F.M., C.M., F.P., M.C., J.D.; writing—original draft preparation, A.M.; writing—review and editing, A.M., F.M.; supervision, A.M., F.M.; project administration,

F.M.; funding acquisition, F.M., C.M., M.C., J.D., F.P. All authors have read and agreed to the published version of the manuscript.

**Funding:** Financial support provided by the US DoE, through the Massie Chair project at University of Turabo, US Department of Defense, under contract W911NF-14-1-0046, and from the Ministerio de Economía y Competitividad (MINECO) of Spain, through the grant ENE2014-57977-C2-1-R, are gratefully acknowledged.

**Acknowledgments:** Technical assistance of I. Poveda from “Servicio Interdepartamental de Investigacion, SIdI” at UAM, is gratefully acknowledged. The facilities provided by the National Center for Electron Microscopy at Complutense University of Madrid (Spain) and the Materials Characterization Center at University of Puerto Rico are gratefully acknowledged.

**Conflicts of Interest:** The authors declare no conflict of interest.

## References

1. Nicoletti G, Arcuri N, Bruno R. A technical and environmental comparison between hydrogen and some fossil fuels. *Energy Convers Manage* 2015; 89, 205 – 13. <https://doi.org/10.1016/j.enconman.2014.09.057>
2. Sherif SA, Barbir F, Veziroglu TN. Towards a Hydrogen Economy. *Electr J* 2005; 18:6, 62 – 76. <https://doi.org/10.1016/j.tej.2005.06.003>
3. Balat M. Potential importance of hydrogen as a future solution to environmental and transportation problems. *Int J Hydrogen Energy* 2008; 33, 4013 – 29. <https://doi.org/10.1016/j.ijhydene.2008.05.047>
4. Valdés A', Qu Z-W, Kroes G-J, Rossmeisl J, Nørskov JK. Oxidation and photo-oxidation of water on TiO<sub>2</sub> surface. *J Phys Chem C* 2008;112:9872e9. <https://doi.org/10.1021/jp711929d>
5. Schley N, Blakemore JD, Subbaiyan NK, Incarvito CD, D'Souza F, Crabtree RH, Brudvig GW. Distinguishing Homogeneous from Heterogeneous Catalysis in Electrode-Driven Water Oxidation with Molecular Iridium Complexes. *J Am Chem Soc* 2011; 133, 10473 – 81. <https://doi.org/10.1021/ja2004522>
6. Etacheri V, Di Valentin C, Schneider J, Bahnemann D, Pillai SC. Visible- light activation of TiO<sub>2</sub> photocatalysts: Advances in theory and experiments. *J Photochem Photobiol C* 2015; 25, 1 – 29. <https://doi.org/10.1016/j.jphotochemrev.2015.08.003>
7. Adleman JR, Boyd DA, Goodwin DG, Psaltis D. Heterogeneous Catalysis Mediated by Plasmon Heating. *Nano Lett* 2012; 9, 4417 – 23. <https://doi.org/10.1021/nl902711n>
8. Banerjee S, Pillai SC, Falaras P, O'Shea KE, Byrne JA, Dionysiou DD. New Insights into the Mechanism of Visible Light Photocatalysis. *J Phys Chem Lett* 2014; 5, 2543 – 54. <https://doi.org/10.1021/z501030x>
9. Mezni A, Mlayah A, Serin V, Smiri LS. Synthesis of hybrid Au-ZnO nanoparticles using a one pot polyol process. *Mater Chem Phys* 2014; 147, 496 – 03. <https://doi.org/10.1016/j.matchemphys.2014.05.022>
10. Luo J, Li D, Yang Y, Liu H, Chen J, Wang H. Preparation of Au/reduced graphene oxide/hydrogenated TiO<sub>2</sub> nanotube arrays ternary composites for visible-light driven photoelectrochemical water splitting. *J Alloy Compd* 2016; 661, 380 – 88. <https://doi.org/10.1016/j.jallcom.2015.11.211>
11. Wang G, Ling Y, Wang H, Lu X, Li Y. Chemically modified nanostructures for photoelectrochemical water splitting. *J Photochem Photobiol C* 2014; 19, 35 – 51. <https://doi.org/10.1016/j.jphotochemrev.2013.10.006>
12. Zhang Y, Ram MK, Stefanako EK, Goswami DY. Synthesis, Characterization, and Application of ZnO Nanowires. *J Nanomater* 2012; 624520, 22. <http://dx.doi.org/10.1155/2012/624520>
13. Kumar PS, Raj MR, Anandan S, Zhou M, Ashokkumar M. Visible light assisted photocatalytic degradation of acid red 88 using Au-ZnO nanophotocatalysts. *Water Sci Technol* 2009; 60, 1589 – 96. <https://doi.org/10.2166/wst.2009.496>
14. Han Z, Wei L, Zhang Z, Zhang X, Pan H, Chen J. Visible-Light Photocatalytic Application of Hierarchical Au-ZnO Flower-Rod Heterostructures via Surface Plasmon Resonance. *Plasmonics* 2013; 8, 1193 – 02. <https://doi.org/10.1007/s11468-013-9531-0>
15. Primo A, Corma A, García H. Titania supported gold nanoparticles as photocatalyst. *Phys Chem Chem Phys* 2011; 13, 886 – 10. <https://doi.org/10.1039/C0CP00917B>
16. Ortega-Méndez JA, López CR, Pulido E, González O, Doña JM, Fernández D, Macías M. Production of hydrogen by water photo-splitting over commercial and synthesized Au/TiO<sub>2</sub> catalysts. *Appl Catal B Environ* 2014; 147, 439 – 52. <https://doi.org/10.1016/j.apcatb.2013.09.029>
17. Donkova B, Vasileva P, Nihtanova D, Velichkova N, Stefano P, Mehandjiev D. Synthesis, characterization, and catalytic application of Au/ZnO nanocomposites prepared by coprecipitation. *J Mater Sci* 2011; 46, 7134 – 43. <https://doi.org/10.1007/s10853-011-5503-y>

18. Yu H, Ming H, Gong J, Li H, Huang H, Pan K, Liu Y, Kang Z, Wei J, Wang D. Facile synthesis of Au/ZnO nanoparticles and their enhanced photocatalytic activity for hydroxylation of benzene. *Bull Mater Sci* 2013; 36, 367 – 72. <https://doi.org/10.1007/s12034-013-0491-y>
19. Bagabas A, Alshammari A, Aboud M, Kosslick H. Room – temperature synthesis of zinc oxide nanoparticles in different media and their application in cyanide photodegradation. *Nanoscale Res Lett* 2013; 8, 519 – 26. <https://doi.org/10.1186/1556-276X-8-516>
20. Cheng P, Yang Z, Wang H, Cheng W, Chen M, Shangguan W, Ding G. TiO<sub>2</sub>-graphene nanocomposites for photocatalytic hydrogen production from splitting water. *Int J Hydrogen Energy* 2012; 37, 2224 – 34. <https://doi.org/10.1016/j.ijhydene.2011.11.004>
21. Haldorai Y, Rengaraj A, Kwak CH, Huh YS, Han YK. Fabrication of nano TiO<sub>2</sub>@graphene composite: Reusable photocatalyst for hydrogen production, degradation of organic and inorganic pollutants. *Synthetic Met* 2014; 198, 10 – 18. <https://doi.org/10.1016/j.synthmet.2014.09.034>
22. Singh GP, Shrestha KM, Nepal A, Klabunde KJ, Sorensen CM. Graphene supported plasmonic photocatalyst for hydrogen evolution in photocatalytic water splitting. *Nanotechnol* 2014; 25, 5701 – 12. <https://doi.org/10.1088/0957-4484/25/26/265701>
23. Tien HN, Luan VH, Hoa L, Khoa NT, Hahn SH, Chung JS, Shi EW, Hur SH. One-pot synthesis of a reduced graphene oxide–zinc oxide sphere composite and its use as a visible light photocatalyst. *Chem Eng J* 2013; 229, 126 – 33. <https://doi.org/10.1016/j.cej.2013.05.110>
24. Ong WJ, Voon SY, Tan LL, Goh BT, Yong ST, Chai SP. Enhanced Daylight-Induced Photocatalytic Activity of Solvent Exfoliated Graphene (SEG)/ZnO Hybrid Nanocomposites toward Degradation of Reactive Black 5. *Ind Eng Chem Res* 2014; 53, 17333 – 44. <https://doi.org/10.1021/ie5027088>
25. Haldorai Y, Shim JJ. Supercritical fluid mediated synthesis of highly exfoliated graphene/ZnO composite for photocatalytic hydrogen production. *Mat Lett* 2014; 133, 24 – 27. <https://doi.org/10.1016/j.matlet.2014.06.150>
26. Zeng D, Gong P, Chen Y, Wang C, Peng DL. Preparation of multi-branched Au-ZnO hybrid nanocrystals on graphene for enhanced photocatalytic performance. *Mater Lett* 2015; 161, 379 – 83. <https://doi.org/10.1016/j.matlet.2015.08.153>
27. Wang P, Wu D, Ao Y, Wang C, Hou J. ZnO nanorod arrays co-loaded with Au nanoparticles and reduced graphene oxide: Synthesis, characterization and photocatalytic application. *Colloids Sur A* 2016; 492, 71 – 78. <https://doi.org/10.1016/j.colsurfa.2015.12.006>
28. Roy P, Periasamy AP, Liana CT, Chang HT. Synthesis of Graphene – ZnO – AuNanocomposites for Efficient Photocatalytic Reduction of Nitrobenzene. *Environ Sci Technol* 2013; 47, 6688 – 95. <https://doi.org/10.1021/es400422k>
29. Lin C, Li Y. Synthesis of ZnO nanowires by thermal decomposition of zinc acetate dihydrate. *Mater Chem Phys* 2009; 113, 334 – 37. <https://doi.org/10.1016/j.matchemphys.2008.07.070>
30. Nejati K, Rezvani Z, Pakizevan R. Synthesis of ZnO Nanoparticles and Investigation of the Ionic Template Effect on Their Size and Shape. *Int Nano Lett* 2011; 1, 75 – 81. <https://doi.org/10.1155/2013/785064>
31. Naldoni A, D'Arienzo M, Altomare M, Marelli M, R Scotti, Morazzoni F, Sellì E, Del Santo V. Pt and Au/TiO<sub>2</sub> photocatalysts for metanol reforming role of metal nanoparticles in tuning charge trapping properties and photoefficiency. *Appl Catal B* 2013; 130, 239 – 48. <https://doi.org/10.1016/j.apcatb.2012.11.006>
32. Machín A, Cotto C, Duconge J, Arango JC, Morant C, Pinilla S, Soto-Vázquez L, Resto E, Márquez F. Hydrogen production via water splitting using different Au@ZnO catalysts under UV-vis irradiation. *Journal of Photochemistry and Photobiology A: Chemistry* 353 (2018) 385–394. <https://doi.org/10.1016/j.jphotochem.2017.11.050>
33. Suryanarayana C, Norton MG. X-ray Diffraction. Plenum Press, New York, 1998.
34. Wen Y, Ding H, Shan Y. Preparation and visible light photocatalytic activity of Ag/TiO<sub>2</sub>/graphene nanocomposite. *Nanoscale* 2011; 3, 4411 – 17. <https://doi.org/10.1039/C1NR10604I>
35. Dang H, Dong X, Dong Y, Huang J. Facile and green synthesis of titanate nanotube/graphene nanocomposites for photocatalytic H<sub>2</sub> generation from water. *Int J Hydrogen Energy* 2013; 38, 9178 – 85. <https://doi.org/10.1016/j.ijhydene.2013.05.061>
36. Briggs, D., and Seah, M. (Eds.), Practical Surface Analysis. Wiley, New York, 1994.
37. Liu H, Xu Q, Yan C, Qiao Y. Corrosion behavior of a positive graphite electrode in vanadium redox flow battery, *Electrochimica Acta*, 56 (2011) 8783. <https://doi.org/10.1016/j.electacta.2011.07.083>

38. Desimoni E, Casella GI, Monroe A, Salvi AM. XPS determination of oxygen-containing functional groups on carbon-fibre surfaces and the cleaning of these surfaces. *Surf. Interface Anal.* 15 (1990) 627. <https://doi.org/10.1002/sia.740151011>
39. Baruah S, Dutta J. Effect of seeded substrates on hydrothermally grown ZnO nanorods. *J Sol-Gel Sci Techn* 2009; 50, 456 – 64. <https://doi.org/10.1007/s10971-009-1917-2>
40. Baruah S, Abbas M, Myint M, Bora T, Dutta J. Enhanced visible light photocatalysis through fast crystallization of zinc oxide nanorods. *Beilstein J Nanotechnol* 2010; 1, 14-20. <https://doi.org/10.3762/bjnano.1.3>
41. Choi WY, Termin A, Hoffmann MR. The role of metal ion dopants in quantum-sized TiO<sub>2</sub>: correlation between photoreactivity and charge carrier recombination dynamics. *J Phys Chem* 1994; 98, 13669-79. <https://doi.org/10.1021/j100102a038>
42. Slamet S, Kusrini E, Salim-Afrozil A, Ibadurrohman M. Photocatalytic hydrogen production from glycerol-water over metal loaded and non-metal doped titanium dioxide. *Int J Technol* 2015; 4, 520-32. <https://doi.org/10.14716/ijtech.v6i4.2176>
43. Bora T, Zoepfl D, Dutta J. Importance of Plasmonic Heating on Visible Light Driven Photocatalysis of Gold Nanoparticle Decorated Zinc Oxide Nanorods. *Sci Rep* 2016; 6: 26913, 1-10. <https://doi.org/10.1038/srep26913>
44. Li L, Yu L, Lin Z, Yang G. Reduced TiO<sub>2</sub>-Graphene Oxide Heterostructure As Broad Spectrum-Driven Efficient Water-Splitting Photocatalysts. *ACS Appl Mater Interfaces* 2016; 8, 8536-45. <https://doi.org/10.1021/acsami.6b00966>
45. Wang Y, Yu J, Wei X, Li Q. Microwave – assisted hydrothermal synthesis of graphene based Au-TiO<sub>2</sub> photocatalysts for efficient visible – light hydrogen production. *J Mater Chem A* 2014; 2, 3847-38. <https://doi.org/10.1039/C3TA14908K>
46. Kolodziejczak A, Jesionowski T. Zinc oxide – From synthesis to application: A review. *Mater* 2014; 7, 2833-81. <https://doi.org/10.3390/ma7042833>
47. Dosado AG, Chen W-T, Chan A, Sun-Waterhouse D, Waterhouse G.I.N. Novel Au/TiO<sub>2</sub> photocatalysts for hydrogen production in alcohol–water mixtures based on hydrogen titanate nanotube precursors, *Journal of Catalysis* 330 (2015) 238–254.
48. Gomes Silva C, Juárez R, Marino T, Molinari R, García H. Influence of Excitation Wavelength (UV or Visible Light) on the Photocatalytic Activity of Titania Containing Gold Nanoparticles for the Generation of Hydrogen or Oxygen from Water. *J. Am. Chem. Soc.* 2011, 133, 3, 595–602. <https://doi.org/10.1021/ja1086358>