

Supplementary Information (SI)

Lipoic acid-functionalized hexanuclear manganese(III) nanomagnets suitable for surface grafting

Marta Orts-Arroyo,^a Carlos Rojas-Dotti,^a Nicolás Moliner^a and José Martínez-Lillo^{*a}

^a *Departament de Química Inorgànica / Instituto de Ciencia Molecular (ICMol), Universitat de València, c/ Catedrático José Beltrán 2, 46980, Paterna, Valencia, Spain. f.jose.martinez@uv.es*




Figure S1. The 2- J coupling exchange model used to fit the experimental magnetic data of **1** and **2**.




Figure S2. Plot of the reduced magnetization ($M/N\mu_B$ vs $\mu_0 H/T$) at the indicated dc fields and temperatures 2–7 K for **1**. The solid lines represent the best fit of the experimental data [$S = 4$, $g = 1.99$ and $D = -0.75$ cm^{-1}].




Figure S3. Plot of the reduced magnetization ($M/N\mu_B$ vs $\mu_0 H/T$) at the indicated dc fields and temperatures 2–7 K for **2**. The solid lines represent the best fit of the experimental data [$S = 4$, $g = 1.99$ and $D = -0.92$ cm^{-1}].